

SPECIFICATION**For****FDLH-0.6/1KV-CCE**

0.6/1(1.2)kV Copper Conductor XLPE Insulated

Polyolefin Sheathed Flame Retardant

with Low Smoke and Zero Halogen Control Cable

(0.6/1(1.2)kV, Cu/XLPE/FR-LSOH)

BY Wachara

(Wachara Sangsomritphon)

MANAGER, Cable Design Section

APP. Winai Ariyasakulsap

(Winai Ariyasakulsap)

MANAGER, Development Department

APP. _____

()

CUSTOMER

Rev.	Date	Description
0	4/6/2020	Issued specification
1	13/11/2020	Add size 3x1.5 mm ² and 25x1.5 mm ²
2	3/02/2021	- Add size - Cancel cable code "0010"
3	5/7/2021	Add size
4	5/7/2021	Add size 2x1, 6x1 mm ² and 30x1 mm ²
5	25/11/2021	Add size 3x1 mm ²
6	27/12/2021	Add size 8x1 and 24x1 mm ²

Customer Document	Rev.
-	

Remark:

This document is based on the Customer Document for the structure and properties of electric wire and cable only. If there are different points, will be shown in deviation table.

1. Scope

This specification covers 1000V copper conductor cross-linked polyethylene (XLPE) insulated polyolefin sheathed flame retardant with low smoke and zero halogen control cable.

The cable shall be based on IEC 60502-1 : 2004 and Amend. 1 : 2009.

The maximum conductor temperature shall be 90°C.

The finished cables shall meet the vertical tray flame test requirements per IEC 60332-1 and IEC 60332-3-24; Category C.

Low smoke test requirements per IEC 61034 and acid gas determinations test requirements per IEC 60754-1 and IEC 60754-2.

2. Conductor

The conductor shall be non-compacted concentric stranded uncoated annealed copper conductor in accordance with IEC 60228 : 2004, Class 2.

The direction of lay shall be left-hand (S) lay.

3. Insulation

The insulation shall be cross-linked polyethylene (XLPE) compound meet the requirements of IEC 60502-1 : 2004.

The average thickness of the insulation shall be not less than that given in Table 1.

The minimum thickness shall be not fall below the value in Table 1 by more than 10% plus 0.1 mm.

4. Cabling

The individual insulated cores shall be cabled together with suitable non-hygroscopic filler to give the completed cable a substantially circular cross section.

The direction of lay shall be left-hand (S) lay.

A suitable binder tape shall be applied helically over the cabled core.

5. Core Identification

The cores shall be identified by colors or by numbers printed on the insulation, as follows:

2-cores : blue, brown

3-cores : brown, black, grey

4-cores : blue, brown, black, grey

For 5-cores to 30-cores :

The cores shall be identified by the arabic numerals printed longitudinally and continuously on the surface of white insulation.

(White color is natural color of XLPE insulation)

6. Sheath

The sheath shall be sunlight resistant, low smoke and zero halogen and flame retardant polyolefin (ST8) compound meet the requirements of the IEC 60502-1 : 2004.


The average thickness of the sheath shall be not less than that given in Table 1.

The minimum thickness shall not fall below the value in Table 1 by more than 20% plus 0.2 mm.

The color of the sheath shall be black.

7. Marking on Cable

The marking items shall be marked with suitable means throughout the length of cable.

1. Manufacturer's name and/or trade mark "  YAZAKI..... : TYE"
2. Year of manufacture
3. Cable property code "FDLH"
4. Rated circuit voltage "0.6/1KV"
5. Type of insulation "XLPE"
6. Type of cable "CONTROL CABLE"
7. Number cores and size of conductor
8. The continuous reel length marking (in figure) shall be made on the sheath at every 1 meter

8. Test and Properties

The cable shall meet the requirements in Test and Inspection and Table 1, when tested in accordance with IEC 60502-1 : 2004 and Amend. 1 : 2009, IEC 60228 : 2004, IEC 60332-1, IEC 60332-3-24; Category C., IEC 61034, IEC 60754-1 and IEC 60754-2.


Remark: Sunlight resistant test meet the requirement of TIS 293-2541.

9. Packing

The cable shall be placed on non-returnable wooden reels.

The reels shall be covered with suitable covering to provide the cable with physical protection during transportation and during ordinary storage and handling operations.

Each reel shall be clearly marked as follows.

1. Designation "FDLH-0.6/1KV-CCE"
2. Number of core and size of cable
3. Cable length
4. Net and gross weight
5. Manufacturer's name and/or trade mark "  **YAZAKI** "
6. Rolling direction of reel

Test and Inspection

Routine Tests

- Maximum conductor resistance, Ohm/km..... specified in Table 1
- AC test voltage for 5 minutes, kV..... 3.5

Sample Tests

- Construction specified in Table 1
- Hot set test at $200\text{ }^{\circ}\text{C} \pm 3\text{ }^{\circ}\text{C}$ for XLPE
 - Maximum elongation under load (%) 175
 - Maximum permanent elongation after cooling (%)..... 15

Type Tests

- Flame retardant tested according to IEC 60332-1 and IEC 60332-3-24; Category C.
- Smoke emission tested according to IEC 61034.
- Halogen gases tested according to IEC 60754-1 and IEC 60754-2.

Definition concerning the tests


Routine tests: Tests made by the manufacturer on each manufactured length of cable to check that each length meets the specified requirements.

Sample tests: Tests made by the manufacturer on samples of completed cable or components taken from a completed cable, at a specified frequency, so as to verify that the finished product meets the specified requirements.

Type tests: Tests made before supplying, on a general commercial basis, a type of cable covered by this standard, in order to demonstrate satisfactory performance characteristics to meet the intended application.

Cable structure

Cross-sectional (Not scale)



No.	Structure	Material
1	Conductor	Non-compacted concentric stranded annealed copper
2	Insulation	Cross-linked polyethylene (XLPE)
3	Filler	Non-hygroscopic
4	Binder tape	PS tape or Suitable tape
5	Sheath	Low smoke and zero halogen flame retardant polyolefin (ST8)

Application: For installed into tray, conduit, underground duct trench or direct burial in ground which provide flame retardant, low smoke and non toxic emission under fire. Maximum conductor temperature of 90 °C for normal operation and 250 °C for short circuit conditions.

Table 1

No. of cores	Size (mm ²)	Conductor (wires/type)	Conductor diameter approx. (mm)	Insulation thickness nominal (mm)	Sheath thickness nominal (mm)	Overall diameter approx. (mm)	Conductor resistance at 20°C maximum (Ohm/km)	Weight of cable approx. (kg/km)	Standard packing length (m)
2	1	7/Non-compacted	1.29	0.7	1.8	10.5	18.1	110	300
2	1.5	7/Non-compacted	1.59	0.7	1.8	11.0	12.1	130	300
2	2.5	7/Non-compacted	2.01	0.7	1.8	12.0	7.41	160	300
3	1	7/Non-compacted	1.29	0.7	1.8	11.0	18.1	130	300
3	1.5	7/Non-compacted	1.59	0.7	1.8	11.5	12.1	150	300
3	2.5	7/Non-compacted	2.01	0.7	1.8	12.5	7.41	190	300
4	1.5	7/Non-compacted	1.59	0.7	1.8	12.0	12.1	180	300
4	2.5	7/Non-compacted	2.01	0.7	1.8	13.5	7.41	240	300
5	1.5	7/Non-compacted	1.59	0.7	1.8	13.0	12.1	210	300
5	2.5	7/Non-compacted	2.01	0.7	1.8	14.5	7.41	270	300
6	1	7/Non-compacted	1.29	0.7	1.8	13.5	18.1	200	300
6	1.5	7/Non-compacted	1.59	0.7	1.8	14.0	12.1	240	300
6	2.5	7/Non-compacted	2.01	0.7	1.8	16.0	7.41	300	300
7	1.5	7/Non-compacted	1.59	0.7	1.8	14.0	12.1	250	300
7	2.5	7/Non-compacted	2.01	0.7	1.8	16.0	7.41	330	300
8	1	7/Non-compacted	1.29	0.7	1.8	14.0	18.1	240	300
8	1.5	7/Non-compacted	1.59	0.7	1.8	15.0	12.1	290	300
8	2.5	7/Non-compacted	2.01	0.7	1.8	17.0	7.41	400	300
9	1.5	7/Non-compacted	1.59	0.7	1.8	16.5	12.1	310	300
9	2.5	7/Non-compacted	2.01	0.7	1.8	18.0	7.41	420	300
10	1.5	7/Non-compacted	1.59	0.7	1.8	17.5	12.1	350	300
10	2.5	7/Non-compacted	2.01	0.7	1.8	19.5	7.41	470	300

Table 1 (continued)

No. of cores	Size (mm ²)	Conductor (wires/type)	Conductor diameter approx. (mm)	Insulation thickness nominal (mm)	Sheath thickness nominal (mm)	Overall diameter approx. (mm)	Conductor resistance at 20°C maximum (Ohm/km)	Weight of cable approx. (kg/km)	Standard packing length (m)
11	2.5	7/Non-compacted	2.01	0.7	1.8	19.5	7.41	490	300
12	1.5	7/Non-compacted	1.59	0.7	1.8	18.0	12.1	390	300
12	2.5	7/Non-compacted	2.01	0.7	1.8	20.0	7.41	550	300
14	1.5	7/Non-compacted	1.59	0.7	1.8	18.5	12.1	420	300
14	2.5	7/Non-compacted	2.01	0.7	1.8	21.0	7.41	600	300
15	1.5	7/Non-compacted	1.59	0.7	1.8	19.5	12.1	450	300
16	1.5	7/Non-compacted	1.59	0.7	1.8	19.5	12.1	470	300
16	2.5	7/Non-compacted	2.01	0.7	1.8	22.0	7.41	700	300
18	1.5	7/Non-compacted	1.59	0.7	1.8	20.5	12.1	500	300
19	2.5	7/Non-compacted	2.01	0.7	1.8	23.0	7.41	750	300
20	1.5	7/Non-compacted	1.59	0.7	1.8	21.0	12.1	550	300
21	1.5	7/Non-compacted	1.59	0.7	1.8	21.5	12.1	600	300
22	1.5	7/Non-compacted	1.59	0.7	1.8	22.5	12.1	650	300
24	1	7/Non-compacted	1.29	0.7	1.8	22.0	18.1	550	300
24	1.5	7/Non-compacted	1.59	0.7	1.8	23.5	12.1	650	300
24	2.5	7/Non-compacted	2.01	0.7	1.8	26.5	7.41	1000	300
25	1.5	7/Non-compacted	1.59	0.7	1.8	23.5	12.1	660	300
26	1.5	7/Non-compacted	1.59	0.7	1.8	23.5	12.1	700	300
30	1	7/Non-compacted	1.29	0.7	1.8	23.0	18.1	700	300
30	1.5	7/Non-compacted	1.59	0.7	1.8	25.0	12.1	800	300