

**SPECIFICATION****For****115KV-CE-CWS (0080)**

115kV XLPE Insulated

Copper Wire Screened

PE Sheathed Power Cable

(115kV, Cu/XLPE/CWS/LAT/PE)

BY Wachara  
(Wachara Sangsomrtiphon)

MANAGER, Cable Design Section

APP. Winai Ariyasakulsap  
(Winai Ariyasakulsap)

MANAGER, Development Department

Rev.	Date	Description
0	2/09/2020	Issued specification
1	22/7/2021	Update reference standard

APP. \_\_\_\_\_  
( )

CUSTOMER

Customer Document	Rev.
-	

**Remark:**

This document is based on the Customer Document for the structure and properties of electric wire and cable only. If there are different points, will be shown in deviation table.

**DESIGNATION : 115KV-CE-CWS (0080)**

**SPEC NO. TYSS 8500 S**

**PAGE No. 1 OF 6**

**REV No. 1**

## **1. Scope**

This specification covers 115KV copper conductor cross-linked polyethylene (XLPE) insulated copper wire screened ribbed polyethylene (PE) sheathed power cable.

The cable shall be in accordance with TIS 2202-2547 (Same IEC 60840 : 2020) and (Reference PEA's specification No. RCBL-015/2552).

## **2. Conductor**

The conductor shall be compacted concentric stranded uncoated annealed copper conductor in accordance with TIS 2427-2552, Class 2. (Same IEC 60228 : 2004, Class 2.)

The direction of lay shall be left-hand (S) lay in the outermost layer.

## **3. Tape on conductor**

The semi-conductive nylon tape as a separator tape shall be longitudinally applied over the conductor.

## **4. Conductor Shield**

The conductor shield shall be a layer of extruded semi-conducting compound, over the conductor.

The average thickness of the conductor shield shall not be less than 1.5 mm.

The minimum thickness of the conductor shield shall not be less than 1.2 mm.

## **5. Insulation**

The insulation shall be unfilled, no carbon black, cross-linked polyethylene (XLPE) compound meet the requirements of TIS 2202-2547. (Same IEC 60840 : 2020)

The average thickness of the insulation shall not be less than that given in Table 2.

The minimum thickness shall not be less than 90 % of the value in Table 2.

The thickness of insulation shall not be included that of conductor shield.

## **6. Insulation Shield**

The insulation shield shall be a layer of extruded semi-conducting compound, over the insulation.

The average thickness of the insulation shield shall not be less than 1.5 mm.

The minimum thickness of the insulation shield shall not be less than 1.2 mm.

## **7. Synthetic Water Blocking Layer**

A semi-conductive non-biodegradable water blocking layer shall be provided under the metallic shield to provide a continuous longitudinal watertight barrier throughout the cable length.

DESIGNATION : 115KV-CE-CWS (0080)

SPEC NO. TYSS 8500 S

PAGE No. 2 OF 6

REV No. 1

#### **8. Metallic Shield**

The metallic shield shall be consist of plain annealed round copper wires applied helically over the water blocking layer.

The contact tape shall be an uncoated annealed copper tape and shall be applied helically with a gap over the copper wire screen.

The thickness of the copper tape shall be approximate 0.1 mm.

#### **9. Synthetic Water Blocking and Cushioning Tape**

A non-conductive non-biodegradable water blocking tape shall be applied over the metallic shield to provide a continuous longitudinal watertight throughout the cable length.

#### **10. Radial Water Barrier**

A radial water barrier consisting of laminated aluminium tape having average thickness at least 0.19 mm. coated on both sides with polyethylene shall be incorporated under the inner sheath.

#### **11. Non-metallic Sheath**

The sheath shall be ribbed type and have one special width rib polyethylene (PE/ST7) compound meet the requirements of TIS 2202-2547. (Same IEC 60840 : 2020)


The average thickness of the sheath shall not be less than the nominal value given in Table 2.

The minimum thickness of the sheath shall not be less than 85 % of the nominal value in Table 2.

The color of sheath shall be black.

#### **12. Marking on Cable**

The marking items shall be provided throughout the cable by inserting identification tape between radial water barrier layer and outer longitudinal water blocking layer.

1. Manufacturer's name and/or trade mark "  YAZAKI..... : TYE"

2. Year of manufacture

3. Rated circuit voltage "115KV"

4. Type of conductor "CU"

5. Type of insulation and sheath "XLPE/PE"

6. Type of cable "POWER CABLE"

7. Size of conductor

8. TIS logo and standard number

9. The purchase contract number

10. The cable length markings shall be made on a special rib through whole length started from "0" with 1 meter increment

**DESIGNATION : 115KV-CE-CWS (0080)**

**SPEC NO. TYSS 8500 S**

**PAGE No. 3 OF 6**

**REV No. 1**

### **13. Test and Properties**


The cable shall meet the requirements in Table 1 and Table 2, when tested in accordance with TIS 2202-2547, TIS 2427-2552 (Same IEC 60840 : 2020, IEC 60228 : 2004) and PEA's specification No. RCBL-015/2552 .

### **14. Packing**

The cable shall be placed on non-returnable steel reels.

The reels shall be covered with suitable covering to provide the cable with physical protection during transportation and during ordinary storage and handling operations.

Each reel shall be clearly marked as follows.

1. Designation "115KV-CE-CWS (0080)"
2. Type of conductor "CU"
3. Type of insulation and sheath "XLPE/PE"
4. Size of conductor
5. Cable length
6. Net and gross weight
7. Year of manufacture
8. Manufacturer's name and/or trade mark "  **YAZAKI** "
9. Rolling direction of reel and cable end position

DESIGNATION : 115KV-CE-CWS (0080)

SPEC NO. TYSS 8500 S

PAGE No. 4 OF 6

REV No. 1

**Table 1**

**Routine Test**

- AC test voltage for 30 minutes, kV ..... 160
- # Maximum partial discharge level ..... 10 pC or better, at 96 kV
- Electrical test on non-metallic sheath ..... Satisfy
- # The partial discharge level shall be no detectable discharge exceeding the declared sensitivity

**Sample Test**

The special tests shall be made on one length from each manufacturing series of the same type and size of cable, but shall be limited to not more than 10% of the number of lengths in the contract, rounded to the upper unity.

- a) Conductor examination and check of dimensions

Maximum conductor resistance, Ohm/km ..... 0.0221

- b) Hot set test at 200 °C  $\pm$  3 °C, 15 minutes, 20 N/cm<sup>2</sup> for XLPE

Maximum elongation under load (%) ..... 175

Maximum permanent elongation after cooling (%) ..... 15

- c) Measurement of capacitance,  $\mu$ F/km ..... 0.228

The capacitance shall be measured between conductor and metallic shield.

The measured value shall not exceed the nominal value declared by the manufacturer by more than 8 %.

DESIGNATION : 115KV-CE-CWS (0080)

SPEC NO. TYSS 8500 S

PAGE No. 5 OF 6

REV No. 1

**Table 2**

No. of core	Size (mm <sup>2</sup> )	Conductor (wires/type)	Conductor diameter (mm)	Conductor shield thickness nominal (mm)	Insulation thickness nominal (mm)	Overall diameter insulation (mm)	Insulation shield thickness nominal (mm)	Copper wire area (mm <sup>2</sup> )	Minimum number of wire screen	Aluminium tape as radial water barrier thickness minimum (mm)	*Sheath thickness nominal (mm)	*Overall diameter (mm)
1	800/95	61/Compacted	34.0 ± 1%	1.5	16.0	69 - 72	1.5	95	70	0.19	3.5	86 - 91

**Table 2 (continued)**

No. of core	Size (mm <sup>2</sup> )	Conductor resistance at 20 °C maximum (Ohm/km)	Capacitance (μF/km)	Weight of cable approx. (kg/km)	Standard packing length (m)
1	800/95	0.0221	0.228	13000	500

\*Excluding rib

DESIGNATION : 115KV-CE-CWS (0080)

SPEC NO. TYSS 8500 S

PAGE No. 6 OF 6

REV No. 1

115kV XLPE Insulated Copper Wire Screened PE Sheathed Power Cable  
(115KV-CE-CWS (0080))

